



Fosroc Conplast P211

Water reducing admixture

Uses

- To improve the effectiveness of the water content of a concrete mix.
- At higher dosages to provide a cost effective means of reducing concrete permeability and thereby reducing water penetration.

Advantages

- Allows specified strength grades to be met at reduced cement content or increased workability.
- Water reduction significantly improves compressive strengths at all ages and enhances durability through the production of low permeability concrete.
- Minimises the risk of segregation and bleeding and assists in the production of a dense, close textured surface, improving durability.
- Chloride free, safe for use in prestressed and reinforced concrete.

Standards compliance

Conplast P211 conforms with BS 5075, BS:EN934-2 and with ASTM C494 as Type A.

Conplast P211 complies with the requirements of the United Kingdom Water Fittings Byelaws Scheme and is listed in the Directory of Materials as suitable for use in contact with potable water under its previous name of Conplast 211.

Description

Conplast P211 is a chloride free water reducing admixture based on selected sugar-reduced lignosulphonates. It is supplied as a brown solution which instantly disperses in water.

Conplast P211 disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively and improving the consistency of the concrete. This produces higher levels of workability for the same water content, allowing benefits such as water reduction and increased strengths to be taken.

Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

Dosage

The optimum dosage of Conplast P211 to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. The normal dosage range is 0.4 to 1.0 litres/100 kg of cementitious material, including PFA, GGBFS and microsilica.

Use at other dosages

Dosages outside the normal ranges quoted above can be used to meet particular mix requirements. Contact Fosroc for advice in these cases.

Effects of overdosing

An overdose of Conplast P211 will result in a significant increase in retardation as compared to that normally obtained at the intended dosage. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased. The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used.

Overdosage may also cause increased air entrainment, which will tend to reduce strength. The degree of this effect will depend on the particular mix design and overdose level.

Typical Properties

Appearance	: Dark Brown Liquid
Specific gravity	: 1.16 at 25°C
Chloride content	: Nil to BS 5075 / BS:EN934
Air entrainment	: Less than 2% additional air is entrained at normal dosages.
Alkali content	: Less than 5.0 g. Na ₂ O equivalent/ litre of admixture.



Fosroc Conplast P211

Instructions for use

Compatibility

Conplast P211 is compatible with other Fosroc admixtures in the same concrete mix. All admixtures should be added to the concrete separately and must not be premixed together prior to addition. The performance of concrete containing more than one admixture should be assessed by trial mixes.

Conplast P211 is suitable for use with all types of Portland cements, SRC cements and cement replacement materials such as PFA, GGBFS and microsilica.

The use of a combination of admixtures in the same concrete mix and or cement replacements may alter the setting time. Trials should always be conducted to determine such setting times.

Dispensing

The correct quantity of Conplast P211 should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact Fosroc for advice regarding suitable equipment and its installation.

Estimating

Supply

Conplast P211

210 litre drum, 1000 litre totes or bulk

For larger users, storage tanks can be supplied.

Storage

Conplast P211 has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then contact Fosroc for advice.

Freezing point: Approximately -3°C



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699
agf@fosroc.com

fax: (+9714) 2859649

email:

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Aman
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4665501

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4664147

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com



Precautions

Health and safety

Conplast P211 does not fall into the hazard classifications of current regulations (see notes 1 and 2 below). However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - **do not** induce vomiting.

For further information consult the Material Safety Data Sheet available for this product.

Fire

Conplast P211 is water based and non-flammable.

Cleaning and disposal

Spillages of Conplast P211 should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

Additional information

Conplast P211 was previously known as Conplast 211.

Note 1: CPL Regulations 1984 Supply- Schedule 1

Note 2: HSE publication Guidance Note EH40

* Denotes the trademark of Fosroc International Limited

† See separate data sheet