



Fosroc Conbextra UW

Non-shrink cementitious grout for underwater installations

Uses

Conbextra UW is used for free flow or pumped grouting applications underwater or in tidal zones. There will be no significant 'wash-out' of the cement phase. Applications include bridge columns, quay pillars, concrete piling, slipways and dams.

Advantages

- No risk of significant 'wash-out' of cement phase when placed underwater.
- Displaces water effectively.
- Gaseous expansion system compensates for shrinkage and settlement in the plastic state.
- High early and ultimate strength and exceptional resistance to freeze-thaw cycling ensure durability of the hardened grout.
- Chloride free.
- Pre-packaged needing only on-site addition of water.

Standards compliance

Conbextra UW meets or exceeds the test requirements of ASTM C 1107.

Description

Conbextra UW is supplied as a ready-to-use powder. The addition of a controlled amount of clean water produces a free-flowing grout. The grout exhibits exceptional resistance to 'washing-out' of the cement phase when placed in stationary or moving water.

Conbextra UW is a blend of cement, graded fine aggregate and chemical additives which impart controlled expansion, water reduction and non 'wash-out' characteristics. The aggregate grading minimises segregation and bleeding whilst assisting the flow characteristics.

Typical Properties

The following results were obtained at a water:powder ratio of 0.22 at 20°C

Test method for Typical result

Compressive strength (BSEN 196-1)

3 days	: 30 N/mm ²
7 days	: 44 N/mm ²
28 days	: 53 N/mm ²

Setting time (BSEN 196-3)

Initial	: 7 - 8 hours
Final	: 9 - 10 hours

Fresh Wet Density : 1800 kg/m³

Expansion characteristics: Controlled expansion occurs in the unset material to ensure that the grout, when cured, will continue to occupy its original volume within the confines of the void in which it was placed

Application instructions

Preparation

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut to a sound base. Substrates which are permanently immersed should be sand-blasted or cleaned with a high pressure water jet. Non-immersed or intermittently immersed substrates can be prepared using these techniques. Alternatively scabbling or bush-hammering may be appropriate.

Formwork

The formwork should be constructed to be leakproof, as Conbextra UW is a free flowing grout, using foam rubber strip or mastic sealant beneath the formwork and between joints. Coat all formwork with Reebol*† to enable easy formwork release.

Mixing and placing

Mixing

For best results, a mechanically powered grout mixer should be used. It is essential that machine mixing capacity and labour availability is adequate to enable the grouting operation to be carried out continuously. This may require the use of a holding tank with provision for gentle agitation to maintain fluidity.

Fosroc Conbextra UW

Measure accurately 4.4 litres of water for each 20 kg bag into the mixer. Slowly add the Conbextra UW whilst mixing continuously. When all the powder is added mix continuously for 5 minutes ensuring a smooth even consistency is obtained. (Fluidity will increase with increased mixing).

Placing

Place the grout within 20 minutes of mixing to gain the full benefit of the expansion process. Continuous grout flow is essential. The mixed grout should be poured or pumped through a flexible tube, having a minimum diameter of 50 mm, to the lowest point in the form. Care must be taken at the start of the grouting operation to restrict the grout flow so that water is not entrapped. The tube may be raised as necessary to reduce any back pressure. It should not be raised above the surface level of the grout.

Conbextra UW can be placed in thicknesses up to 75 mm in one pour when used above water. When used underwater, the heat sink effect in this environment will allow thicknesses of up to 150 mm to be placed. For thicker sections, up to 200 mm above water and 400 mm underwater, it is necessary to fill out Conbextra UW using a clean rounded well graded aggregate ranging from 2 to 10 mm. The ratio of aggregate added to Conbextra UW should not exceed 1:1 by weight. For such mixes a concrete mixer should be used. Unrestrained surface area should be kept to a minimum.

Curing

Curing will not be required in intermittently or totally submerged situations. However, when cast above water, exposed areas should be thoroughly cured with Concure curing membrane, continuous application of water and/or wet hessian.

Cleaning

Because of its water resisting properties, equipment used for Conbextra UW will be difficult to clean. The use of hot water for cleaning purposes will assist. Cured material can be removed mechanically or with Fosroc Acid Etch**.

Limitations

Conbextra UW must not be applied below 5°C.

Estimating

Supply

Conbextra UW : 20 kg bags

Yield

Conbextra UW : Approx 11.6 litres when mixed with 4.4 litres of water

Note: Allowance should be made for wastage when estimating quantities required.

Storage

Conbextra UW has a shelf life of 12 months if kept in a dry store in sealed bags. If stored in high temperature and high humidity locations, the shelf life may be reduced.

Precautions

Health and safety

Conbextra UW contains cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately — **do not** induce vomiting.

Fire

Conbextra UW is non-flammable.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

