

## Acrylic floor sealer and concrete curing membrane

### Uses

To provide a sealing coat on cementitious floors such as concrete, granolithic screed, cementitious Terazzo and stamped concrete. Also provides dustproof and more easily cleaned surface with resistance to the penetration of various liquids. Ideal for dust proofing warehouses, garages, indoor car parks and light industrial buildings. It can also be used as a curing membrane on freshly placed concrete.

### Advantages

- Simple brush or spray application
- Prevents dusting by sealing the surface
- Durable finish offers good resistance to abrasion
- Cures and seals the floor in a single operation

### Standards compliance

Nitoflor FC100 complies with ASTM C309.

### Description

Nitoflor FC100 single pack, penetrating synthetic acrylic coating has excellent adhesion to cementitious surfaces and, when cured, forms a semi-gloss flexible film.

It is supplied ready for use direct from the can and is available in a range of colours.

### Specification

#### Floor sealer

The floor sealer shall be Nitoflor FC100, a single component, acrylic floor sealer. The sealer shall be applied in a minimum of two coats at a coverage rate of between 4 and 8m<sup>2</sup> per litre per coat.

#### Concrete curing membrane

The curing membrane shall be Nitoflor FC100 a single component acrylic sealer which complies with ASTM C309. The sealer shall be applied in one coat at a coverage rate of 4-5m<sup>2</sup> per litre.

### Technical support

Fosroc offers a comprehensive range of high performance, high quality flooring, jointing and repair products for both new and existing floor surfaces. In addition, Fosroc offers a technical support package to specifiers, end users, and contractors, as well as on-site technical assistance in locations all over the world.

### Properties

The values given below are average figures achieved in laboratory tests. Actual values attained on site may show minor variations from those quoted.

#### Physical properties at 20°C

<b>Time between coats</b>	: 2 hours minimum
<b>Initial hardness</b>	: 6 hours

#### Chemical properties

Nitoflor FC100 is resistant to a range of chemicals. For further information, contact the local Fosroc office.

Good housekeeping is essential in areas where chemical spillage is likely to occur. It is especially important that such spillage should not be allowed to dry since very much higher concentrations of chemicals may result.

### Instructions for use

#### Preparation

##### *New concrete floors*

The product can be applied by roller or spray when the surface water has disappeared after the final finishing operation, or the following day while the concrete is still green. Nitoflor FC100 requires no preparation before application on new concrete floors, except when bleed water leads to laitence.

##### *Old concrete floors*

A sound, clean substrate is essential to achieve maximum adhesion. Dry removal of laitence by use of mechanical methods is preferable. Oil and grease penetration should be removed by the use of a proprietary chemical degreaser or by hot compressed air treatment.

Minor defects in concrete surfaces such as pinholes should be repaired with Dekguard Filler. If thicker repairs or re-profiling should be required, use Renderoc BF2 or Renderoc SXtra, depending on the thickness.

#### Application

Nitoflor FC100 can be applied by brush, spray, squeegee or roller. A continuous coating of uniform thickness should be achieved. A minimum of two coats are recommended. Allow at least two hours drying time between coats.

#### Cleaning

Nitoflor FC100 should be removed from tools and equipment using Fosroc Solvent 102\* immediately after use.

# Fosroc Nitoflor FC100

## Maintenance

The service life of a floor can be considerably extended by good housekeeping practices. Regular cleaning of Nitoflor FC100 may be carried out using a rotary scrubbing machine with a water miscible cleaning agent, or by hot water washing at temperatures up to 50°C.

## Limitations

- The durability of Nitoflor FC100 is reduced in areas of very heavy foot traffic such as around work benches, drinks machines, doorways etc. It is advisable to either:
  - a) Specify additional coats in such areas or
  - b) Specify a higher build system such as Nitoflor FC150\*† in such areas.
- Nitoflor FC100 is not suitable for use in areas where hydrocarbon or solvent spillage is likely to occur.

## Estimating

### Supply

Nitoflor FC100	:	20 litre packs
Fosroc Solvent 102	:	5 litre cans

### Coverage

Nitoflor FC100	:	4-8 m <sup>2</sup> /litre/coat
----------------	---	--------------------------------

**Note:** The coverage figures given are theoretical – due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

## Storage

When stored in dry conditions between 10°C and 30°C, away from sources of heat and naked flames, in the original unopened packs, Nitoflor FC100 has a shelf life of 12 months. If stored at high temperatures the shelf life will be reduced.

Nitoflor FC100 should be protected from frost.

## Precautions

## Health and safety

Nitoflor FC100 and Fosroc Solvent 102 should not come in contact with skin and eyes, or be swallowed. Avoid inhalation of vapour/spray. Use only in well ventilated areas. If working in confined areas, suitable respiratory protective equipment must be worn. Wear suitable protective clothing, gloves and eye/face protection. Barrier creams provide additional skin protection.

Should accidental skin contact occur, remove with a suitable skin cleanser, followed by washing with soap and water. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately – **do not** induce vomiting.

## Fire

Nitoflor FC100 and Fosroc Solvent 102 are flammable. Store in accordance with national and local fire prevention regulations. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO<sub>2</sub> or foam. Do not use a water jet.

## Flash points

Nitoflor FC100	:	40°C
Fosroc Solvent 102	:	33°C

## Disposal

Spillages of component products should be absorbed onto earth, sand or other inert material and transferred to a suitable vessel. Disposal of such spillages or empty packaging should be in accordance with local waste disposal regulations.

For further information, refer to the Product Safety Data Sheet.

\* Denotes the trademark of Fosroc International Limited

† See separate data sheet



## Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

### Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: [agf@fosroc.com](mailto:agf@fosroc.com)

### Regional offices

Abu Dhabi, Al Gurg Fosroc  
Bahrain, YBA Kanoo  
Kuwait, Boodai  
Oman, Al Amanah  
Qatar, Tadmur

telephone: 673 1779  
telephone: 17738200  
telephone: 4817618  
telephone: 24815080  
telephone: 4432365

fax: 673 1449  
fax: 17732828  
fax: 4832124  
fax: 24817554  
fax: 4419517

email: [abudhabi@fosroc.com](mailto:abudhabi@fosroc.com)  
email: [bahrain@fosroc.com](mailto:bahrain@fosroc.com)  
email: [kuwait@fosroc.com](mailto:kuwait@fosroc.com)  
email: [oman@fosroc.com](mailto:oman@fosroc.com)  
email: [qatar@fosroc.com](mailto:qatar@fosroc.com)

## Al Gurg Fosroc LLC

Post Box 657, Dubai  
United Arab Emirates

[www.fosroc.com](http://www.fosroc.com)

