



Fosroc Conplast RP264

Retarding water reducing admixture

Uses

- To improve the effectiveness of the water content of a concrete mix.
- To help maintain the workability of readymixed concrete deliveries in hot weather.
- To extend working times of concrete.
- Particularly suitable for use in mixes with low cohesion.

Advantages

- Water reduction significantly improves compressive strengths at all ages and enhances durability.
- Controlled retardation extends working life and stiffening time for ease of construction.
- Control of stiffening improves slip forming and assists in preventing the formation of cold joints in large pours.
- Minimised transportation delay problems maintains placeability and reduces the risk of pump blockage.
- Slight air entrainment improves cohesion in mixes with poorly graded sands or a lack of fine material, minimising bleed and segregation.
- Allows specified strength grades to be met at reduced cement content or increased workability.
- Chloride free, safe for use in prestressed and reinforced concrete.

Standards compliance

Conplast RP264 conforms with BS 5075, BS:EN 934-2, ASTM C494 as Type B and D.

Description

Conplast RP264 is a chloride free water reducing admixture based on selected lignosulphonate materials. It is supplied as a brown solution which instantly disperses in water.

Conplast RP264 disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively. The initial hydration of the cement is also delayed, resulting in a delay in the setting time of the concrete with no adverse effect on subsequent stiffening and strength gain.

Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

Typical Dosage

The optimum dosage of Conplast RP264 to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. The normal dosage range is 0.3 to 0.8 litres/100 kg of cementitious material, including PFA, GGBFS or microsilica.

Use at other dosages

Dosages outside the normal range quoted above can be used to meet particular mix requirements. Contact Fosroc for advice in these cases.

Effects of overdosing

An overdose of Conplast RP264 will result in a significant increase in retardation as compared to that normally obtained at the intended dosage. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased. The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used.

Overdosage may also cause increased air entrainment, which will tend to reduce strength. The degree of this effect will depend on the particular mix design and overdose level.

Typical Properties

Appearance	: Dark Brown liquid
Specific gravity	: 1.17 @ 25°C
Chloride content	: Nil to BS 5075 / BS:EN934
Air entrainment	: Less than 2% additional air is entrained at normal dosages.

Instructions for use

Retardation

The level of retardation obtained may be varied by altering the dosage of Conplast RP264 used, which will also alter the level of water reduction obtained. Retardation is also affected by factors other than the admixture, depending on the mix details and conditions involved. Major factors include the following:

- Cement replacement materials and SRC cements will usually give greater levels of retardation than concrete mixes made with ordinary Portland cement at the same admixture dosage.

Fosroc Conplast RP264

- b) High temperatures will require increased dosages to obtain the same change in stiffening time compared to a control mix.
- c) Changes in cement content, source or chemistry may lead to variations in the retardation obtained. The amount of tri-calcium aluminate in the cement has been identified as being one of the main contributory factors in this respect, with a lower level leading to greater retardation.
- d) The use of a combination of admixtures in the same concrete mix may alter the setting time. Trials should always be conducted to determine such setting times.

Compatibility

Conplast RP264 is compatible with other Fosroc admixtures in the same concrete mix. All admixtures should be added to the concrete separately and must not be premixed together prior to addition. The performance of concrete containing more than one admixture should be assessed by trial mixes.

Conplast RP264 is suitable for use with all types of Portland cements, SRC cements and cement replacement materials such as PFA, GGBFS and microsilica.

The use of a combination of admixtures in the same concrete mix and or cement replacements may alter the setting time. Trials should always be conducted to determine such setting times.

Dispensing

The correct quantity of Conplast RP264 should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact Fosroc for advice regarding suitable equipment and its installation.

Estimating

Supply

Conplast RP264

210 litre drum, 1000 litre totes or bulk

For larger users, storage tanks can be supplied.

Storage

Conplast RP264 has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then contact Fosroc for advice.

Freezing point: Approximately -4°C

Precautions

Health and safety

Conplast RP264 does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - **do not** induce vomiting.

For further information consult the Material Safety Data Sheet available for this product.

Fire

Conplast RP264 is water based and non-flammable.

Cleaning and disposal

Spillages of Conplast RP264 should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4665501

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4664147

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

