



Fosroc Conplast SP470

Superior high range water reducer specifically designed for superplasticised high performance concrete

Uses

- Specifically formulated for use in high performance as well as normal concrete.
- Recommended for low slump concrete to produce more uniform, predictable and consistent concrete.
- To provide early and ultimate strength gain by significantly reducing water content in a concrete mix
- To provide improved durability by increasing ultimate strengths and reducing concrete permeability.
- To significantly improve the workability and retention of site mixed concrete without increasing water demand
- Specifically developed for use in high quality concrete mixes utilising cement replacements.
- Ideally suited for factory-line concrete production including applications using cement replacement materials and white cement.
- Can be used for effective dispersion in coloured concrete.
- Can be used in semi-dry conditions

Advantages

- High range water reducing property helps achieve high early-strengths and low water absorption values.
- High early strengths help in reducing production cycles
- Reduced permeability levels even for low slump concrete especially in the case of the precast elements, which reduces penetration of water and other deleterious impurities and increases the durability of concrete. Also reduces efflorescence.
- Improves cohesion and particle/pigment dispersion to produce dense concrete matrix.
- Chloride free, suitable for use in precast, prestressed and reinforced concrete.
- Compatible with all portland cements including cement replacement materials and white cement.
- Helps in superior concrete finishes which increase life of moulds.
- Can help in moderate slump retention.

Standards compliance

Conplast SP470 conforms with BS 5075, BS:EN 934-2 and with ASTM C494 as Type G, depending on dosage used.

Description

Conplast SP470 is chloride free, superplasticising admixture based on selected synthetic and organic polymers.

Conplast SP470 disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively. The very high levels of water reduction possible allow major increases in strength to be obtained. Special slump retainers help to retain workability also.

Typical Properties

Appearance	: Brown liquid
Specific gravity	: 1.21 @ 25° C
Chloride content	: Nil to BS 5075 / BS:EN934
Air entrainment	: Less than 2% additional air is entrained at normal dosages.

Instructions for use

Mix design

Where the main requirement is to retain workability over considerable period of time and to improve strengths, initial trials should be made with normal concrete mix designs.

The addition of the admixture will allow the removal of water from the mix whilst maintaining workability. After initial trials, minor modifications to the overall mix design may be made to optimise performance.

Compatibility

Conplast SP470 is compatible with other Fosroc admixtures used in the same concrete mix. All admixtures should be added to the concrete separately and must not be mixed together prior to addition. The resultant properties of concrete containing more than one admixture should be assessed by trial mixes.

Conplast SP470 is suitable for use with all types of Portland cements and cement replacement materials such as PFA, GGBFS, metakaolin and microsilica.

The use of a combination of admixtures in the same concrete mix and or cement replacements may alter the setting time. Trials should always be conducted to determine such setting times.

Dispensing

The correct quantity of either Conplast SP470 should be measured by means of a recommended dispenser.

Normally, the admixture should then be added to the concrete with the mixing water to obtain the best results. These admixtures are not recommended to be added in dry

Fosroc Conplast SP470

aggregates or cement. It should always be added in wet mix conditions. Full blending of the admixture and the concrete should be ensured by mixing at high speed for a period of at least two minutes. Contact Fosroc for advice regarding suitable equipment and its installation.

Typical dosage

The optimum dosage of Conplast SP470 to meet specific requirements should always be determined by trial mixes using the materials and conditions that will be experienced in use. For normal concrete a dosage between 0.75% to 1.5% by weight of cement may be used, and for high performance concrete, dosage between 1.5% to 2.5% by weight of cement may be used.

Use at other dosages

Dosages outside the typical ranges quoted above can be used to meet particular requirements, contact Fosroc for advice.

Effects of overdosing

An overdose of double the amount of Conplast SP470 will result in a slight increase in slump retention and retardation. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased. The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials is used. Overdosage may also cause increased air entrainment, which will tend to reduce strength. The degree of this effect will depend on the particular mix design and overdose level.

Cleaning and disposal

Spillages of Conplast SP470 should be absorbed onto sand, earth or vermiculite and transferred to

suitable containers. Remnants should be hosed down with large quantities of water. The disposal of excess or waste material should be carried out in accordance with local

legislation under the guidance of the local waste regulatory authority.

Estimating

Supply

Conplast SP470

210 litre drum, 1000 litre totes or bulk

For larger users, storage tanks can be supplied.

Storage

Conplast SP470 should be re-circulated two-three times a day for 20 - 30 minutes and has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range contact Fosroc for advice.

Freezing point: Approximately -2°C

Health and safety

Conplast SP470 does not fall into the hazard classifications of current regulations (see notes 1 and 2 below). However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - **do not** induce vomiting. For further information consult the Material Safety Data Sheet available for this product.

Fire

Conplast SP470 is water based and nonflammable.

Note 1: CPL Regulations 1984 Supply- Schedule 1

Note 2: HSE publication Guidance Note EH40

* **Denotes the trademark of Fosroc International Limited**



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 1773200
telephone: 4817618
telephone: 24815080
telephone: 4665501

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4664147

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

