

Non-shrink, high strength, highly fluid cementitious precision grout

Uses

Conbextra HF PLUS is used for free flow precision grouting in a wide range of heavy duty applications, such as :

- Machine base plates
- Gas or steam turbines
- Bridge bearings
- Crane rails
- Generators, Presses, Milling machines
- Anchor bolts & rods
- Column bases
- Precast elements

Advantages

- Non-shrink.
- Unique non-metallic dual expansion system compensates for shrinkage in both the plastic and hardened states.
- Excellent initial flow and flow retention.
- High early strength facilitates rapid installation and early operation of plant.
- High ultimate strength and low permeability ensure durability of the hardened grout.

- Hydrogen-free gaseous expansion.
- Chloride free.
- Suitable for pumping or pouring over a large range of application consistencies and temperatures.

Standards compliance

Conbextra HF PLUS is suitable for use in contact with potable water.

Conbextra HF PLUS meets or exceeds the test requirements of ASTM C 1107.

Description


Conbextra HF PLUS is supplied as a ready-to-use pre-bagged dry powder. The addition of a controlled amount of clean water produces a free-flowing precision grout for gap thicknesses from 10 to 150 mm. In addition the low water requirement ensures high early strength and long term durability.

Conbextra HF PLUS is a blend of Portland cements, graded fillers and chemical additives which impart controlled expansion in both the plastic and hardened states. The filler grading minimises segregation and bleeding over a wide range of application consistencies.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Figure 1 : Typical specification drawing



Fosroc Conbextra HF PLUS

Typical Properties

The following results were obtained at a water:powder ratio of 0.16 and a temperature of 23°C.(+ or - 2)

Test method for	Typical result
Compressive strength	
BS 1881 part 116 1983	: 30 N/mm ² @ 1 day 50 N/mm ² @ 3 days 65 N/mm ² @ 7 days 80 N/mm ² @ 28 days
Flow	
ASTM C1437-01	: Greater than 150%
Bleed ASTM C940	: Nil
Setting time	
ASTM C191-01a	:
Initial set	: 8 - 9 hours @23°C
Final set	: 10 - 11 hours @23°C
Fresh wet density	: Approx. 2,200 kg/m ³
BS 1881:107:1983	
Modulus of elasticity	
ASTM C 469-02	: >22,000MPa
Expansion characteristics	: Upto 1% in accordance with ASTM C 940:98a
Chloride Permeability	
ASTM C 1202:19)	: Very low

Specification

Supplier specification

Where mentioned on the contract documents, all precision grouting (specify details and areas of application) must be carried out using Conbextra HF PLUS manufactured by Fosroc and used in accordance with the manufacturer's data sheet.

Performance specification

All precision grouting (specify details and areas of application) must be carried out with a pre-packaged cement based product, which is non-metallic and chloride-free.

It shall be mixed with clean water to the required consistency and not exhibit bleed or segregation.

A volumetric expansion of up to 2% shall occur while the grout is in a plastic state by means of a gaseous, hydrogen-free system. The grout must also be compensated for shrinkage in the hardened state.

The compressive strength of the grout must exceed 50 N/mm²

at 7 days and 65 N/mm² at 28 days.

The storage, handling and placement of the grout must be in strict accordance with the manufacturer's instructions.

Instructions for use

Preparation

Concrete surface

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes and fixing pockets must be blown clean of any dirt or debris.

Pre-soaking

For a minimum of 2 hours prior to grouting, the area of cleaned substrate should be flooded with fresh water. Immediately before grouting takes place, any free water should be removed. Particular care should be taken to blow out all bolt holes and pockets.

Base plate

It is essential that this is clean and free from oil, grease or scale. Air pressure relief holes should be provided to allow venting of any isolated high spots.

Levelling shims

If these are to be removed after the grout has hardened, they should be treated with a thin layer of grease.

Formwork

The formwork should be constructed to be leakproof as Conbextra HF PLUS is a free flowing grout. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints.

In some cases it is practical to use a sacrificial semi-dry sand and cement formwork. The formwork should include outlets for the pre-soaking water.

Unrestrained surface area

This must be kept to a minimum. Generally the gap width between the perimeter formwork and the plate edge should not exceed 75 mm on the pouring side and 25 mm on the opposite side. There should be no gap at the flank sides.



Fosroc Conbextra HF PLUS

Mixing

For best results a mechanically powered grout mixer should be used. For quantities up to 60 kg a slow speed drill fitted with a Fosroc Mixing Paddle (MR3) should be used. Larger quantities will require a high shear vane mixer. Do not use a colloidal impeller mixer.

It is essential that machine mixing capacity and labour availability is adequate to enable the grouting operation to be carried out continuously. This may require the use of a holding tank with provision for gentle agitation to maintain fluidity.

Consistency of mixed grout

To achieve the consistencies the amount of clean water that is added to a 25 kg bag at 20°C is:

Figure 2: Typical hopper system

Flowable	: 4 litres for 25 kg bag
Fluid	: 4.5 litres for 25 kg bag

The selected water content should be accurately measured into the mixer. Slowly add the total contents of the Conbextra HF PLUS bag, mix continuously for 5 minutes, ensuring a smooth, even consistency is obtained.

Maximum flow distance at 20°C

Grout consistency	Gap depth mm	Max. flow distance in mm	
		100 mm head	250 mm head
Flowable	: 10	360	1200
	20	950	2600
	30	1500	3000
	40	2200	3000+
	50	3000	3000+
Fluid	: 10	900	2500
	20	1900	3000
	30	3000	3000+
	40	3000+	3000+

Placing

At 25°C, place the grout within 15 minutes of mixing to gain the full benefit of the expansion process.

Conbextra HF PLUS can be placed in thicknesses up to 125 mm in a single pour.

Any bolt pockets must be grouted prior to grouting between the substrate and the base plate.

Continuous grout flow is essential. Sufficient grout must be available prior to starting and the time taken to pour a batch must be regulated to the time taken to prepare the next one.

The mixed grout should be poured only from one side of the void to eliminate the entrapment of air or surplus pre-soaking water. This is best achieved by pouring the grout across the shortest distance of travel. The grout head must be maintained at all times so that a continuous grout front is achieved.


Where large volumes have to be placed Conbextra HF may be pumped. A heavy duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps may also be suitable.

Curing

On completion of the grouting operation, exposed areas should be thoroughly cured. This should be done by the use of Concure curing membrane, or continuous application of water and/or wet hessian.

Cleaning

Conbextra HF PLUS should be removed from tools and equipment with clean water immediately after use. Cured material can be removed mechanically, or with Fosroc Acid Etch**.



Fosroc Conbextra HF PLUS

Sampling procedure

Cementitious grouts cannot be tested as concrete. Special sampling procedure are required. Refer to your local Fosroc office for further details.

High temperature working

It is suggested that, for temperatures above 35°C, the following guidelines are adopted as good working practice:

- (i) Store unmixed material in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- (ii) Keep equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come into direct contact with the material itself.
- (iii) Try to eliminate application during the hottest times of the day and in direct sunlight.
- (iv) Make sufficient material, plant and labour available to ensure that application is a continuous process.
- (v) Water (below 20°C) should be used for mixing the grout prior to placement

Limitations

- In general, grouts should not be placed in any unrestrained situation, i.e. base plate plinths, etc. Failure to comply may lead to crack development in the grout. However they can be used for bolt pockets. In doubt, please consult your local Fosroc offices for more details.

Estimating

Supply

Conbextra HF PLUS : 25 kg bags

Yield

Flowable : 13.15 litres / 25 kg

Fluid : 13.5 litres / 25 kg

Note: Allowance should be made for wastage when estimating quantities required.

Storage

Conbextra HF PLUS has a shelf life of 12 months if kept in a dry store in sealed bags. If stored in high temperature and high humidity locations the shelf life will be reduced.

Precautions

Health and safety

Conbextra HF PLUS is alkaline and should not come into contact with skin and eyes. Avoid inhalation of dust during mixing. Gloves, goggles and dust mask should be worn.

If contact with skin occurs, wash with water. Splashes to eyes should be washed immediately with plenty of clean water and medical advice sought.

Fire

Conbextra HF PLUS is non-flammable.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17732820
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

