



Fosroc Nitoproof 100

Bituminous protective coating

Uses

Nitoproof 100 is designed to provide a continuous barrier to the passage of water and water vapour and can be used to produce vapour barriers, damp proof courses, linings to potable water tanks and pipes, below ground concrete protection, concrete curing by water retention, and corrosion protection to metal surfaces.

Advantages

- Single component
- Easily and inexpensively applied; high coverage rate
- Tough and resistant to most naturally occurring chemicals
- Does not taint water
- Can be applied to damp concrete substrates
- Quick drying
- Excellent adhesion to most common building substrates
- Excellent water retention for use as a curing compound
- Successfully used for over 30 years in a wide range of environments

Standards compliance

Nitoproof 100 complies with BS 3416:1991 Type 1A Appendix B General performance for bituminous coating, and ASTM C309 water retention requirements for curing membranes.

Description

Nitoproof 100 low viscosity blend of selected bitumens in solvent dries to form a high quality tough bitumen film. Nitoproof 100 can be applied by brush, roller or spray equipment to prepared surfaces for a variety of purposes.

Properties

result	Test method	Typical
Drying time	: BS3900:C2:1972	2 1/2 hours
Flexibility	: BS3416:1975	Pass
Chloride protection	: BS3416:1975	Pass
Performance	: BS3416:1991 Appendix B	Pass
Overcoating time	: 3 hours (min)	

Instructions for use

Preparation

Surfaces must be clean, dry, free from oil, grease and all loosely adhering particles such as rust, mill scale, mortar and cement laitence. These should be carefully removed by wire or stiff brushing and finally soft brushing or filtered compressed air to remove dust.

Oil and grease should be removed by the use of a proprietary degreasing agent. For optimum adhesion to steel, grit blasting to SA2 1/2 is recommended.

Nitoproof 100 can be applied to damp concrete, brick and plaster surfaces provided there is no free surface water or bleed. A test patch is recommend where there is doubt.

Application

Stir thoroughly prior to use.

Damp-proof membranes, vertical vapour barriers

Apply a full coat of Nitoproof 100 and allow to dry. Coverage rate should be approximately 3m² per litre. Apply a second coat of Nitoproof 100 at right angles to the first coat.

Water tank and pipe line protection

Two coats of Nitoproof 100 should be applied as detailed above. Where necessary the coating can be thickened at floor/wall corners by forming a 20x20mm fillet onto the first coat of Nitoproof 100 and liberally coating with a second coat of Nitoproof 100.

Concrete screeds or render

Where it is necessary to cover the membrane with a screed or render, clean grit 2mm nominal size should be broadcast into the wet second coat to provide a mechanical key.

All loose grit should be removed prior to placing the screed/ render. (Care should be taken to ensure that the membrane is not damaged during placing of the screed).

Curing compound

Apply two coats of Nitoproof 100 as for damp proof membranes. This will give a curing efficiency in excess of 80% and comply with ASTM C309. Nitoproof 100 can be applied to damp concrete.

Fosroc Nitoproof 100

Repairs

Damaged areas of Nitoproof 100 can be readily overcoated to restore the continuity of the membrane.

Cleaning

Tools and equipment should be cleaned with Fosroc Solvent 102 immediately after use.

Limitations

Application should not commence if the temperature of the substrate is below 6°C or above 45°C.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Estimating

Supply

Nitoproof 100	:	20 and 200 litre drums
Fosroc Solvent 102	:	5 litre cans
Fosroc Chemical Degreaser	:	25 litre cans

Coverage

Nitoproof 100	:	2.0-7.0m ² /litre per coat depending upon substrate porosity and smoothness.
----------------------	---	---

To comply with ASTM C309, 2 coats are required at 3m² per litre per coat.

Storage

Nitoproof 100 will have a minimum shelf life of 12 months if stored in normal warehouse conditions between 15 and 40°C. Protect from temperatures below 10°C. Store away from direct sources of heat or naked flames.

Precautions

Health and safety

Some people are sensitive to resins and solvents so gloves and a barrier cream such as Kerodex Antisolvent, Rozalex Antipaint, Debba-Wet Work or similar should be used when handling these products. Remove contamination from the skin with soap and water or a resin removing cream such as Kerocleanse Standard Grade Skin Cleanser or Rozaklens Industrial Skin Cleanser. Follow by washing with soap and water. **Do not** use solvent. The use of goggles is recommended but should accidental eye contamination occur, wash thoroughly with plenty of water and seek medical treatment immediately.

Nitoproof 100 contains solvents. Avoid breathing the vapours and ensure good ventilation. Replace lid when not in use. Soak up any spillage with sand or sawdust.

Fire

Nitoproof 100 and Fosroc Solvent 102 are flammable. Ensure adequate ventilation. Do not use near a naked flame and do not smoke during use.

Flash points

Nitoproof 100	:	37°C
Fosroc Solvent 102	:	33°C

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

