



# Fosroc Nitoproof UVR Topcoat

**Colour stable, fire retardant, flexible polyurethane coating**

## Description

Fosroc Nitoproof UVR Topcoat is a roller applied, two-component, high solids, flexible, light to medium-duty trafficable, colour stable and flame retardant polyurethane coating.

## Uses

- Colour stable and fire rated topcoat component for the Fosroc Nitoproof 800 roof/balcony waterproofing system
- Colour stable and fire rated topcoat for the Fosroc Polyurea WPE waterproofing system

Please refer to the Fosroc Nitoproof 800 system data sheet, or the Fosroc Polyurea WPE product data sheet and Fosroc Polyurea Method Statement for further information, including surface preparation detail.

## Advantages

- Environment friendly – high solids
- Seamless and monolithic, including field joints
- Significantly enhances the durability of reinforced concrete when used in conjunction with either Nitoproof 800 system or Fosroc Polyurea WPE
- Colour stable
- Strong adhesive bond
- Long open time for use with Fosroc Polyurea – can be applied up to 48 hours after polyurea application \*
- Fire rated to BS476-3:EXT.F.AA when used in conjunction with the Fosroc Nitoproof 800 system
- Fire rated to BS476-3:EXT.F.AA when used in conjunction with Fosroc Polyurea WPE

\* for applications >48 hours after polyurea application, reactivation is required – see Fosroc Polyurea data sheet and Fosroc Polyurea Method Statement

## Colours and Opacity

A minimum film thickness of 0.3mm is required for use with Nitoproof 800HT system, and a minimum film thickness of 0.2mm for use with Fosroc Polyurea WPE.

For a list of standard colours please consult your local Fosroc office.

## Properties

### Typical Physical properties at 23°C

Density at 25°C : 1.5 – 1.6 g/ml

Abrasion, ASTM D4060 (1kg, CS10 wheels) : 0.4 g /1000 cycles \*

Chemical Resistance : Resistant to spillage of various chemicals including Motor oil, Kerosene, Diesel and Petrol. Consult your local Fosroc office for specific details

Service temperature : -30°C to +70°C

\* as 0.2mm thickness coating on Fosroc Polyurea WPE

## Application Instructions

Pour and drain the full contents of the hardener container into the resin container and mix thoroughly with a slow speed electric stirrer fitted with an appropriate paddle, for a minimum of 3 minutes until homogeneous. DO NOT dilute the product under any circumstances.

Spread and apply at the required coverage rate (see Coverage) using a roller to achieve a uniform finish. A broadcast of dried sand may be used to provide anti-slip feature (coloured sand may be used for aesthetic effect). Allow to dry. Walkable after approximately 12 hours at 20°C.

Working Life, 20°C \* 15 - 20 mins

Tack-Free Time, 20°C 8 hours

Overcoating Time, 20°C 8 - 48 hours

### Trafficable, 20°C

Light Duty Traffic 12 hours

Service Traffic 2 - 3 days

\* Usable working life of material following mixing and spreading as per the application instructions.

## Recoating

For recoating/repair applications, if the existing Nitoproof UVR Topcoat coating has been allowed to dry >48 hours, then a surface reactivation should be carried out using a Fosroc Nitoprime 150 wipe, and allowed to dry before applying the recoating, approximately 30 minutes at 20°C. Refer to your local Fosroc office for advice.



constructive solutions

# Fosroc Nitoproof UVR Topcoat

## Estimating

### Supply:

Plastic containers : 5 kg, 10 kg packs

### Coverage:

On Fosroc Nitoproof 800HT : 22 m<sup>2</sup> per 10 kg pack for 0.3 mm film

On Fosroc Polyurea WPE : 32 m<sup>2</sup> per 10 kg pack for 0.2 mm film \*

\* Coverage rate given above, is a minimum. A higher coverage rate may be required in some cases, depending on site conditions such as surface profile.

## Limitations

Do not proceed with application if atmospheric relative humidity is >90% or if the surface temperature is <3°C above the dew point.

Application should not commence when the substrate temperature or the ambient temperature is, or is anticipated to be, <+5°C during the application or within the tack-free period.

For work in exposed areas, do not proceed with application if precipitation is imminent. Keep applied areas protected from precipitation within the tack-free period.

The manufacture of Fosroc Nitoproof UVR Topcoat is a batch process and despite close manufacturing tolerances, colour variation may occur between batches. Fosroc recommends using Nitoproof UVR Topcoat from a single batch as the final finish in one area section.

As with all exterior coatings, some fading of colour can be expected over time, depending on UV levels and temperature.

## Safety handling

Avoid contact with eyes and skin. Wear suitable protective clothing, gloves and eye/face protection at all times. Ensure adequate ventilation.

Fosroc Nitoproof UVR Topcoat hardener may cause sensitisation by skin contact.

In case of eye contact, first aid must be administered immediately. The eyes should be held open while flushing with a continuous low pressure stream of water for at least 15 minutes. Seek medical advice immediately. If swallowed, seek medical attention immediately - do not induce vomiting.

The use of barrier creams provides additional skin protection.

Refer to safety data sheets for detailed information.

## Storage

Fosroc Nitoproof UVR Topcoat has a shelf life of 12 months if kept in a dry, air conditioned store between +5°C and +30°C in the original unopened containers.

## Disposal Considerations

Cured Nitoproof UVR Topcoat can be disposed of without restriction. The uncured base and hardener components should be disposed of according to local environmental laws and ordinances.

"Drip free" containers should be disposed of according to local environmental laws and ordinances.

Refer to safety data sheets for all relevant information on Fosroc Nitoproof UVR Topcoat.

## Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. Fosroc is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

## Additional Information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring products

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray-grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/ anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office.

Fosroc and Nitoproof are trademarks of Fosroc International Limited.



### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.

## Al Gurg Fosroc LLC

Post Box 657, Dubai  
United Arab Emirates

telephone:  
(+9714) 2039699

fax:  
(+9714) 2859649

email:  
[aqf@fosroc.com](mailto:aqf@fosroc.com)

[www.fosroc.com](http://www.fosroc.com)

Registered Office: 215 Community, Street No. 13, Nad Al Hamar Road, Al Ramool Industrial Estate, Rashidiya, Dubai



UAE/0755/12/A