



Fosroc Supercast SW30

(Formerly Supercast SW20Plus)

High swell hydrophilic waterstop for in-situ concrete

Uses

Integral sealing for construction joints in concrete cast in-situ where high swell performance is demanded, such as in highly saline ground conditions.

Convenient and problem solving in situations where a conventional waterstop would require complex shuttering.

Typical uses include secant piled and diaphragm walled basements, pile caps and casting against old concrete.

Supercast SW30 can provide simple solutions to detailing pipe entries, construction joints in the vertical plane and to kicker joints.

Can be linked to Supercast PVC** waterstops to give an effective combination of waterstops which maintain network continuity.

Advantages

- Easy to install
- Supercast SWX swellable adhesive enables full integration of Supercast SW30 with Supercast PVC networks.
- Solves detailing problems in conjunction with Supercast PVC range
- Swelling properties unaffected by long term wet/dry cycling
- Performs effectively in saline ground conditions
- Sustains effective seal in wet conditions

Standards compliance

Suitable for use in contact with potable water - Water Byelaws Scheme Approved product.

Description

Supercast SW30 is a swellable waterstop that can be installed and positively linked into conventional Supercast PVC waterstop networks.

This allows the use of Supercast PVC for expansion joints and Supercast SW30 for construction joints, all the time maintaining an integrated network.

Supercast SW30 is made from high performance synthetic elastomer strips. The high swelling action is the result of contact between water and hydrophilic groups which are part of the Supercast SW30 'Basic Polymer' molecular structure.

The hydrophilic groups are not subject to extraction or loss of swelling performance by prolonged or repeated wetting. This is a unique feature of the basic polymer. Expansion of the waterstop creates a positive pressure against the face of the concrete joint, thus preventing water passing through the protected joint.

Design criteria

Supercast SW30 should be used to prevent the passage of water through non-movement joints in both new in-situ concrete and between new and existing concrete. Supercast SW30 increases in volume in the range of up to 500% and gives a resistance to hydraulic heads of up to 100 metres.

Swelling of Supercast SW30 in fresh concrete is minimal, therefore maximising the positive pressure to seal the joint.

Supercast SW30 is suitable for application between existing and newly placed concrete where there is little or no steel continuity and where up to 2mm movement may occur.

Supercast SW30 waterstops should be positioned to ensure that a minimum of 100 mm cover of concrete is present to accommodate pressure developed during the swelling process.

Properties

Form	:	Green or Black rectangular section elastomeric strips
Size	:	10mm X 20mm
Solids content	:	100%
Unrestrained volumetric expansion	:	Up to 500%
Application temperature range	:	-20° to 50°C
Service temperature range	:	-30° to 70°C
Hydrostatic pressure resistance	:	100 metres (10 bar)
Watertightness	:	Seals up to 2mm gap if used in conjunction with Supercast SWX or Supercast SW Adhesive

Specification

Supplier specification

Water swellable - Basic Polymer - hydrophilic waterstop (and attachments) where shown on the drawings, shall be Fosroc Supercast SW30 obtained from Fosroc. It shall be used in accordance with the manufacturer's current application instructions.

Fosroc Supercast SW30

Performance specification

Water swellable - Basic Polymer - hydrophilic waterstop, where shown on the drawings, shall be made from a preformed elastomeric strip which can integrate into existing waterstop networks. It shall be free from rubber, bentonite or other inclusions. The waterstop shall have an unrestrained volumetric expansion of upto 500%. It must not deteriorate under prolonged wet/dry cycling. It must be able to withstand a hydrostatic head of 100 metres (10 bar). It shall be used in accordance with the methods given in the manufacturer's current data sheet.

Instructions for use

Supercast SW30 may be positioned by bonding with either Supercast SWX or Supercast SW Adhesive. The waterstop may be installed either into a groove cast in the concrete or directly onto the concrete surface.

Limitations

- Supercast SW30 should not be used for expansion joints or those subject to significant repetitive movements.
- Supercast SW30 should not be installed with less than 100 mm of concrete cover to ensure that the pressure arising from the swelling action is accommodated.
- Supercast SW30 should not be used in locations which allow free unrestrained swelling.
- Installation using nailing is not recommended as nails can damage the concrete.

Estimating

Supply

Supercast SW30 : 5 m rolls

Storage

When stored in cool dry conditions, away from sunlight, in the original, unopened containers Supercast SW products have a shelf life of 12 months.

Precautions

Health and safety

There are no health hazards associated with Supercast SW30 in normal use.

Ancillary materials

Supercast SWX

Form	:	Elastomeric water swellable paste
Colour	:	Grey
Tack free time	:	Approx 1hour (20°C/50% RH)
Cure rate	:	3mm in 24 hours
Volume swell ratio	:	200%
Concrete pour	:	2 to 8 hours
Adhesion	:	Can be used on damp concrete provided it is rag dry.

Supercast SW Adhesive

Form	:	Grey paste
Application temperature	:	5°C to 30°C
Maximum open time	:	30 mins
Concrete pour	:	2 to 8 hours
Adhesion	:	Can be used on damp concrete provided it is rag dry.

The above data represents typical values and should not be considered as a purchase specification



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

