

Skid resistant, flexible, waterproof protection flooring system

Uses

Trafficguard UREP is a modified polyurethane-based traffic deck system designed to provide an added level of protection to, new and existing, heavily trafficked areas such as:

- Car parks
- Industrial manufacturing units
- Warehouses

Advantages

- Flexible and tear resistant
- Waterproof
- Seamless
- Rapid application, reliable and safe
- Available in a range of colours

Description

Trafficguard UREP is a multi-layer deck protection system comprising a primer, flexible waterproof intermediate coat & top coat using Nitoflor FC150. All components are applied in the liquid phase and react chemically to form a tough, flexible, waterproof, protective surface.

Properties

Intermediate coat

Elongation (ASTM D412)	: > 300%
Tensile Strength (ASTM D412)	: 4 N/mm ²
Tear Resistance (ASTM D624)	: 15 N/mm
Crack Bridging ability (ASTMC1305)	: Pass

Instructions for use

Surface Preparation

New concrete surfaces should have reached 80% of their intended physical properties - generally only achieved after a minimum curing period of 28 days. Existing concrete surfaces must be prepared to provide a clean, sound substrate.

Surfaces should be clean and dry with open capillary, free from laitance, oil & grease, curing compounds or other surface contaminants which may prevent full and proper adhesion of the primer. All blowholes, and other surface undulations greater than 1 mm in depth, should be repaired using Nitomortar FC(B)*†.

Temperature of the substrate during application must be between 5°C and 40°C.

Priming

Apply Trafficguard Primer to the prepared surface at a wet film thickness of 200 microns.

Whilst Trafficguard Primer is still wet, seed with Fosroc Anti Slip Grain No. 3 at a rate of 0.4 kg / m² and allow to cure for 24 hours.

Application

Intermediate Coat

Apply Trafficguard Intermediate Coat to the primed surface at a wet film thickness of 200 - 500 microns. For best results the Intermediate Coat should be applied with a notched trowel or squeegee.

Whilst the Intermediate coat is still wet apply Fosroc Anti Slip Grain No. 1200 at a rate of 0.4 kg / m². Allow to cure for 12 hours prior to applying the wear course.

Nitoflor FC150

Apply Nitoflor FC150 to the Intermediate coat at a wet film thickness of 200 microns. Allow to cure for 24 hours prior to trafficking.

Cleaning

Tools and equipment should be cleaned with immediately after use with Fosroc Solvent 102*.

Fosroc Trafficguard UREP

Estimating

Supply

Trafficguard Primer	: 9 litre packs
Trafficguard Intermediate Coat	: 18 litre packs
Nitoflor FC150	: 4.5 litre packs
Antislip Grains No. 1200, 3	: 25 kg bags

Coverage

Trafficguard Primer	: 5.0 m ² /litre
Trafficguard Intermediate Coat	: 2 - 5 m ² /litre
Nitoflor FC150	: 5 .0 m ² /litre
Antislip Grains No. 1200, 3	: 0.4 kg / m ²

Note: The above coverage rates are given for guidance only as actual quantities used will vary depending upon the nature of substrate and conditions on site.

Storage

Shelf life

When stored in warehouse conditions at less than 25°C, Trafficguard UREP will have a shelf life of 12 months. Avoid storage of material under direct sunlight.

Technical Support

Fosroc offers a full technical support package to specifiers, end users and contractors, as well as on-site assistance in locations all over the world.

Limitations

- Do not proceed with application if precipitation is imminent, temperatures are expected to drop below 7°C within 24 hours of application.
- Trafficguard UREP should not be applied onto substrate known to suffer from rising dampness, having R.H. greater than 75% as measured in accordance with BS 8203 Appendix A or having moisture content greater than 5% as measured by a Hammond concrete/mortar moisture tester (type COCO).

- Do not proceed with application if an osmotic condition is known or is suspected to exist.
- This system should not be applied when exposed to UV.

Precautions

Health and safety

Trafficguard Primer, Intermediate Coat and Nitoflor FC150 and Fosroc Solvent 102 should not come in contact with skin or eyes, nor should they be swallowed. Avoid inhalation of vapours and ensure adequate ventilation.

Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye/face protection. Barrier creams such as Kerodex Antisolvent or Rozalex Antipaint provide additional skin protection.

Should accidental skin contact occur, remove immediately with a resin removing cream such as Kerocleanse Standard Grade Skin Cleanser or Rozaklens Industrial Skin Cleanser, followed by washing with soap and water - **do not** use solvent.

The use of goggles is recommended, in case of accidental eye contamination, rinse immediately with plenty of water and seek medical advice.

If swallowed seek medical attention immediately - **do not** induce vomiting.

Fire

Fosroc Solvent 102 and Trafficguard Intermediate coat are flammable. Do not use near a naked flame.

Flash points

Fosroc Solvent 102	: 33°C
Trafficguard Intermediate Coat	: 33°C

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com